

**TECHNICAL DATA**

<b>CHARACTERISTICS</b>	<b>VALUES</b>	
Reaction to fire	CLASS A1	
Flexural strength	Lower expected value :	8,3 MPa
	Mean value:	10,6 MPa
	Standard deviation :	2,1 MPa
Slip resistance	SRV dry:	Luc. = 53 units
	SRV wet:	Luc. = 4 units
Tactility	This characteristic shall be declared where subject to regulatory requirements or upon request. The tactility is expressed by a description of surface corrugation obtained by mechanical finishes.	
Absorption	Mean value	1,6%
Apparent density	P 2,57 Mg/m <sup>3</sup>	
Frost resistance	Mass loss F = 2,9 %	Category CE FT3
Medium compressive strenght	Lower expected value	130,5 MPa
	Highest value	168,6 MPa
	Mean value:	152 MPa